

ALPHA® 620

Mildly Activated Liquid Rosin Flux

DESCRIPTION

ALPHA 620 is a type of RMA flux superior in fluxing strength as demonstrated by meniscograph and solder spread testing. **ALPHA 620** Flux meets the applicable RMA requirements of MIL-F-14256 D.

ALPHA 620 is recommended for use where a very effective, yet non-corrosive flux is desired.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

APPLICATION GUIDELINES

ALPHA 620 is designed for wave, spray and dip application.

TECHNICAL DATA

Item	Typical Values	Item	Typical Values
Appearance	Clear Amber	Flash Point (T.C.C.)	16.7 °C
Solids Content, wt/wt	37%	Water Extract Resistivity	182,000 ohm-cm
Specific Gravity @ 25 °C (77 °F)	0.887 ± 0.005	Shelf Life (from Date of Mfg.)	
Pounds per Gallon @ 25 °C (77 °F)	7.38	Flux Type (MIL-F-14256 D)	RMA



RECYCLING SERVICES

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area or link here.



SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available at MacdermidAlpha.com/assembly-solutions/knowledge-base.**

CONTACT INFORMATION

To confirm this document is the most recent version, please contact Assembly@MacDermidAlpha.com

www.macdermidalpha.com

North America
109 Corporate Blvd.
South Plainfield, NJ 07080, USA

1.800.367.5460

EuropeUnit 2, Genesis Business Park
Albert Drive
Woking, Surrey, GU21 5RW, UK
44.01483.758400

Asia
8/F., Paul Y. Centre
51 Hung To Road
Kwun Tong, Kowloon, Hong Kong
852.3190.3100

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDemid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.

