

ALPHA[®] EF-2202

VOC-Free No-Clean Flux

DESCRIPTION

ALPHA EF-2202, is a VOC-free, halide-free, rosin/resin-free, low solids no-clean flux which provides the highest activity of any VOC-free Bellcore compliant flux for defect-free soldering. It is formulated with a proprietary mixture of organic activators which deliver excellent wetting and top-side hole fill, even with OSP coated bare copper boards which have undergone prior thermal excursions. Several proprietary additives are also formulated into **ALPHA EF-2202** which act to reduce the surface tension between the solder mask and the solder; thereby, dramatically reducing the tendency of solderball generation. The formulation of **ALPHA EF-2202** is also designed to be more thermally stable; thereby, reducing the occurrence of solder bridging.

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

FEATURES AND BENEFITS

- Bellcore compliant for assemblies requiring this standard.
- VOC-free to help meet air quality regulations.
- Exceptional wetting for excellent hole-fill even with OSP coated bare copper boards, with prior reflows.
- Thermally stable activators provide low solder bridging.
- Reduces the surface tension between solder mask and solder to provide low solderball frequency.
- Suitable for selective soldering process.
- Very low level non-tacky residue to reduce interference with pin testing and good board cosmetics.

APPLICATION GUIDELINES

Preparation - To maintain consistent soldering performance and electrical reliability, it is important to begin the process with circuit boards and components that meet established requirements for solderability and ionic cleanliness. It is suggested that assemblers establish specifications on these items with their suppliers and that suppliers provide Certificates of Analysis with shipments and/or assemblers perform incoming inspection. A common specification for the ionic cleanliness of incoming boards and components is 5 µg/in² maximum, as measured by an Omegameter with heated solution.

Care should be taken in handling the circuit boards throughout the process. Boards should always be held at the edges. The use of clean, lint-free gloves is also recommended.

Conveyors, fingers and pallets should be cleaned. Bioact SC-10 Solvent Cleaner has been found to be very useful for these cleaning applications.

Flux Application – ALPHA EF-2202 is formulated to be applied by spray method. When spray fluxing, the uniformity of the coating can be visually checked by running a piece of cardboard over the spray fluxer or by processing a board-sized piece of tempered glass through the spray and then through the preheat section.

General Guidelines for Machine Settings	
Operating Parameter	Typical Level
Amount of Flux Applied	Spray: <1200 µg/in ² of solids
Top-Side Preheat Temperature	220 to 235 °F (104 to 113 °C)
Bottomside Preheat Temperature	0 to 40 °F (0 to 22 °C) vs. Top-Side
Recommended Preheat Profile	Straight ramp to desired top-side temperature
Maximum Ramp Rate of Topside Temperature (to avoid component damage)	2°C/second (3.5°F/second) maximum
Conveyor Angle	5 to 8° (6° most common)
Conveyor Speed	3.5 to 6.5 feet/minute (1.0 to 1.8 meters/minute)
Contact Time in the Solder (includes Chip Wave and Primary Wave)	1.5 to 4.0 seconds (2 to 3 seconds most common)
Solder Pot Temperature:	
Sn63/Pb37 Alloy	465 to 500 °F (240 to 260 °C)
Lead-Free Alloys (99.3Sn/0.7Cu, 96.5/3.5Ag, 95.5Sn/4.0Ag/0.5Cu)	490 to 510 °F (255 to 265 °C)

General Guidelines for Machine Settings	
Operating Parameter	Typical Level
These are general guidelines which have proven to yield excellent results; however, depending upon your equipment, components, and circuit boards, your optimal settings may be different. In order to optimize your process, it is recommended to perform a design experiment, optimizing the most important variables (amount of flux applied, conveyor speed, topside preheat temperature, solder pot temperature and board orientation).	

Flux Solids Control - If rotary drum spray fluxing, the flux solids will need to be controlled via thinner addition, in this case DI water, to replace evaporative losses of the flux solvent. As with any flux with less than 5% solids content, specific gravity is not an effective measurement for assessing and controlling the solids content. The acid number should be controlled to between 28.0 and 32.0. Alpha's Flux Solids Control Kit #3, a digital titrator, is suggested. Request Alpha's Reference Bulletin for details on the kit and titration procedure. When operating a rotary drum fluxer continuously, the acid number should be checked every eight hours. Over time, debris and contaminants will accumulate in recirculating type flux applicators. For consistent soldering performance, dispose of spent flux every 40 hours of operation. After emptying the flux, the reservoir should be thoroughly cleaned with DI water.

Residue Removal – ALPHA EF-2202 is a no-clean flux and the residues are designed to be left on the board. If desired, flux residues can be removed with EC Ultra Semi-aqueous cleaner or with other commercially available solvent cleaners.

Touch-Up/Rework - Use of the Cleanline Write Flux Applicator with NR205 flux and Telecore Plus cored solder is recommended for hand soldering applications.

TECHNICAL DATA

Item	Typical Values	Item	Typical Values
Appearance	Clear, Colorless Liquid to pale yellow	pH, as is	2.4
Solids Content, wt/wt	3.5	Recommended Thinner	DI Water
Specific Gravity @ 25 °C (77 °C)	1.012 ± 0.003	Shelf Life	18 months
Acid Number (mg KOH/g)	30.0 ± 2.0	VOC Content (ASTM D2369)	1.5 %
Flash Point (T.C.C.)	None	IPC J-STD-004 Designation	ORL0

CORROSION & ELECTRICAL TESTING
Corrosion Testing

Test	Requirements	Results
Silver Chromate Paper ¹ IPC-TM 650 Test Method 2.3.33	No detection of halide	Pass
Copper Mirror Tests ¹ (Modified IPC/Bellcore Method)	No complete removal of copper	Pass
Copper Corrosion Test IPC-TM 650 Test Method 2.6.15	No evidence of corrosion	Pass

J-STD-004 Surface Insulation Resistance

Test	Conditions	Requirements ²	Results ²
"Comb-Down" Uncleaned	85 °C/85% RH, 7 days	1.0 x 10 ⁸ minimum	6.8 x 10 ⁹
"Comb-Up" Uncleaned	85 °C/85% RH, 7 days	1.0 x 10 ⁸ minimum	6.2 x 10 ⁹
Control Boards	85 °C/85% RH, 7 days	2.0 x 10 ⁸ minimum	1.3 x 10 ¹⁰
IPC Test Condition (per J-STD-004): -50V, measurement @ 100V/IPC B-24 board (0.4mm lines, 0.5mm spacing).			

Bellcore Surface Insulation Resistance

Test	Conditions	Requirements ²	Results ²
"Comb-Down" Uncleaned	35 °C/85% RH, 5 days	1.0 x 10 ¹¹ minimum	3.0 x 10 ¹¹
"Comb-Up" Uncleaned	35 °C/85% RH, 5 days	1.0 x 10 ¹¹ minimum	2.2 x 10 ¹²
Control Boards	35 °C/85% RH, 5 days	2.0 x 10 ¹¹ minimum	1.1 x 10 ¹²
Bellcore Test Condition (per GR 78-CORE, Issue 1): 48 Volts, measurement @ 100V/25 mil lines/50 mil spacing.			

Bellcore Electromigration

Test Condition	SIR (Initial)	SIR (Final)	Requirement	Result	Visual Result
"Comb-Up" Uncleaned	3.2×10^{10}	1.1×10^{11}	SIR (Initial)/SIR (Final) <10	Pass	Pass
"Comb-Down" Uncleaned	1.2×10^{11}	1.4×10^{11}	SIR (Initial)/SIR (Final) <10	Pass	Pass
Bellcore Test Condition (per GR 78-CORE, Issue 1): 65 °C/85% RH/500 Hours/10V, measurement @ 100V/IPC B-25B Pattern (12.5 mil lines, 12.5 mil spacing).					

¹ **Copper Mirror** and **Silver Chromate Paper** tests were performed using flux sample prepared by reconstituting with isopropyl alcohol after evaporation of its water vehicle at 80 °C for one hour as per footnote 1 or corrosion testing table.

² All values shown are in ohms.

RECYCLING SERVICES

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area or [link here](#).



SAFETY & WARNING

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available at MacdermidAlpha.com/assembly-solutions/knowledge-base.**

STORAGE

Keep from freezing. Store between 0 to 25 °C

CONTACT INFORMATION

**To confirm this document is the most recent version, please contact
 Assembly@MacDermidAlpha.com
www.macdermidalpha.com**

<p>North America 109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.367.5460</p>	<p>Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400</p>	<p>Asia 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100</p>
---	--	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.