

# STAYSTIK® 701

## Alumina Filled “Low Flow” Dielectric Paste

### DESCRIPTION

These thermoplastic adhesive pastes are designed for use in a variety of electronic applications. These materials are ideal for applications where resistance to high temperature excursions is desired. These paste adhesives can be used for die attach in solder sealed, hermetic packages and have demonstrated low RGA moisture readings. This high temperature, reworkable thermoplastic system offers many unique advantages in applications traditionally ill-suited to thermoset adhesives.

**Fully Polymerized Resin – No “Cure”**  
**Easily Reworkable – No Outgassing**  
**Bonds in Seconds – Not in Hours or Minutes**  
**Low Modulus Reduces Stress to Bonded Materials**

READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

### TYPICAL PROPERTIES

Typical Properties	101	211	301	701
Filler Material	Silver	AlN	None	Alumina
Continuous Use Range	-65 to 200 °C	-65 to 200 °C	-65 to 200 °C	-65 to 200 °C
Max Excursion Temperature	400 °C	400 °C	400 °C	400 °C
Thermal Conductivity (W/M <sup>2</sup> K)	≥ 3.0	≥ 1.0	≤ 0.25	≤ 0.6
Volume Resistivity (Ohm-cm)	≤ 5 x 10 <sup>-4</sup>	≥ 1 x 10 <sup>+9</sup>	≥ 1 x 10 <sup>+9</sup>	≥ 1 x 10 <sup>+9</sup>
Die Shear Adhesion @25 °C	≥ 3500 psi	≥ 3000 psi	≥ 3500 psi	≥ 3500 psi
Elastic Modulus (psi)	≥ 360,000	≥ 360,000	≥ 360,000	≥ 360,000
Viscosity (Brookfield RTV @ 2.5 RPM)	97.5 to 202.5 kcps	145 to 235 kcps	36.4 to 67.6 kcps	TBD
Glass Transition Temp. (Tg)	180 to 185 °C	180 to 185 °C	180 to 185 °C	180 to 185 °C

Typical Properties	101	211	301	701
Shelf Life @ 25 °C	1 Year	1 Year	1 Year	1 Year

### PASTE CHARACTERISTICS

These products are supplied at a rheology suitable for screen printing. Use a stainless steel screen with a 60 to 105 mesh count and a backside emulsion build-up of 0.5 to 6.0 mils. After screening, the paste can be dried at 120 to 150 °C for 15 to 30 minutes.

After drying, substrates can be stored for long periods of time at room temperature in ambient conditions (although dry box storage is recommended) without altering the properties of the adhesive. For silver filled paste expect a wet to dried thickness reduction in the Z-axis of approximately 30 to 40%. For Aluminum nitride, aluminum oxide, filled and non-filled pastes, expect a wet to dried thickness reduction of approximately 60 to 70%.

Deposition via syringe is also possible. Standard syringe sizes available are 3cc, 5cc, 10cc, and 30cc. Equipment best suited to dispensing these materials incorporates a mechanical or vacuum pull-back, anti-tailing feature.

### BONDING

Bond pre-dried deposits at 300 to 375°C. Pressure required is dependent on temperature and dwell time at temperature. Lower temperatures require higher pressures. Higher temperatures require little or no pressure. It is critical that both interfaces to be bonded reach the required temperature. Typical pressures for most applications range from 1 to 10 psi. Time required to form a bond will depend on the application. Bonds can be formed in seconds under optimum conditions. Typical recommended bond times are 10 to 60 seconds. Equipment used for heating can range in sophistication from a hot plate to a box oven or continuous feed belt furnace.

It is possible to perform "zero pressure" attachment of small components and die by placing them directly in the wet deposited material. It is necessary to control the heating ramp rate in order to slowly volatilize the solvent system. Typically, the ramp rate should be 10 °C per minute or less with a peak temperature of 350 °C and a dwell time at the peak temperature of at least 10 minutes.

**SAFETY & WARNING**

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use. **Safety Data Sheets are available.**

**STORAGE**

Store at room temperature (25 °C). Do not freeze. Shelf life of sealed, unopened jars is one year. If the material is kept beyond the recommended shelf life, it is not necessarily unusable. But, a quality control should be performed on the properties relevant to the application.

**CONTACT INFORMATION**

To confirm this document is the most recent version, please contact  
[techinfo@MacDermidAlpha.com](mailto:techinfo@MacDermidAlpha.com)

[www.macdermidalpha.com](http://www.macdermidalpha.com)

<p><b>North America</b> 3950 Johns Creek Ct, Suite 300 Suwanee, GA 30024 USA 908.791.2300</p>	<p><b>Europe</b> Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400</p>	<p><b>Asia</b> 14 Joo Koon Crescent, Singapore 629014 65.6430.0700</p>
---	--	--

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE . Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.