


# **AUTOSTAT WP20**

**Heat Stabilized White Polyester** 

#### PRODUCT DESCRIPTION

**Autostat WP20** is a heat stabilised white opaque polyester\* film with a primer coating on one surface. The primed surface has a higher gloss level than the untreated surface. The film has a very low transparency and high brightness; it is therefore particularly suitable as a versatile print medium, offering outstanding high mechanical strength and good dimensional stability.



\* The term polyester is the generic term for several different polymers, of which polyethylene terephthalate (PET) is the most common. PET is used in MacDermid Enthone polyester products.

#### READ ENTIRE TECHNICAL DATA SHEET BEFORE USING THIS PRODUCT

#### **PRODUCT RANGE**

Product	Gauge	Version
Autostat WP – heat stabilised opaque white, pre-primed polyester film	490 μm	WP20



# **TECHNICAL DATA SHEET**

#### **TYPICAL PROPERTIES**

Property	Typical Value	Test Method	
Tensile strength <sup>1</sup>	MD ≥ 95 N / mm <sup>2</sup> TD ≥ 100 N / mm <sup>2</sup>	ISO 527-1-3	
Whiteness (Berger) <sup>1</sup>	≥ 95, ≤ 130	ASTM E 308 Method A	
Color <sup>1</sup> L* a* b*	≥ 94.5, ≤ 99 ≥ -0.5, ≤ +0.3 ≥ -5.5, ≤ -1.5	ISO 7724	
Thermal stability (130°C) <sup>2</sup>	MD < 0.150% TD < 0.03%	Test Method 017	
Coefficient of Linear thermal expansion <sup>1</sup>	2 x 10 <sup>-5</sup> K <sup>-1</sup>	-	
Film thickness <sup>2</sup>	490 μm ± 40 μm, to nearest whole μm	Test method PLAWP 003	
Density <sup>1</sup>	1.395 g / cm <sup>3</sup>	ASTM D 1505-68 Method C	
Roughness R value <sup>1</sup>	45 nm	DIN 4762	

Note: All evaluation results are obtained from lab produced samples at MacDermid Alpha Electronics Solutions. They are for general guidance only and do not represent the final product's properties.

#### **PRIMER**

**Autostat WP** has an ink adhesion primer on one surface. The primed surface has a higher gloss level than the untreated surface.

The primer offers excellent adhesion to a wide range of solvent inks, but it is recommended that the customer verifies that the adhesion of their own ink is fit for purpose.

Technical Data Sheet CPI-00023/4 Issue: 04 January 2023

<sup>&</sup>lt;sup>1</sup> Data derived from base film manufacturer's literature

<sup>&</sup>lt;sup>2</sup> Specification value



## **TECHNICAL DATA SHEET**

#### **SHELF LIFE & STORAGE CONDITIONS**

The recommended shelf life is 36 months from the date of manufacture. MacDermid Enthone guarantees a minimum remaining shelf life of 8 weeks at the time of despatch.

The recommended shelf life represents the maximum processing lifetime of the product from the date of manufacture when stored correctly and in unopened packaging.

The following storage conditions are recommended:

Storage Conditions		
Temperature	15 to 25 °C	
Relative Humidity	50 to 65%	
Packaging	Store in original protective packaging Once the packaging has been opened, the processing lifetime can be compromised due to air ingress, contamination or UV light	
Moisture	Store away from water sources	
Chemicals	Keep away from aggressive solvents	
Stacking	For material ≤ 250 µm thick, 100 sheet packs should be stacked no more than 10 packs high	

# **IMDS ID-No**

By arrangement with our regulatory affairs team.



### **TECHNICAL DATA SHEET**

#### **SAFETY & WARNING**

It is recommended that the company/operator read and review the Safety Data Sheets for the appropriate health and safety warnings before use.

Safety Data Sheets are available.

#### **WASTE TREATMENT**

Prior to using any recommendations or suggestions for waste treatment, the user is required to know the appropriate local/state/federal regulations for on-site or off-site treatment which may require permits. If there is any conflict regarding our recommendations, local/state/federal regulations take precedent.

#### **CONTACT INFORMATION**

# To confirm this document is the most recent version, please contact techinfo@MacDermidAlpha.com

www.macdermidalpha.com

North America 245 Freight Street Waterbury, CT 06702, USA +1 203 575 5700 **Europe**Grove Road, Wantage
OX12 7BZ, United Kingdom
+44 1235 771111

**Asia**26 Tuas West Road
Singapore, 638382
+65 6862 3327

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US +1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazii 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory, Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product tailure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates thereform. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "(R)" and "TM" are registered trademarks or trademarks of MacDermid, Inc. and its group of companies in the United States and (or other countries).

Technical Data Sheet CPI-00023/4 Issue: 04 January 2023